

According to EU Directive 1907/2006

#### **Product name: ABS-PRO** Date of issue: 31-05-2018

Version: 1.3

1. Identification of the substance/preparation and of the company

- 1.1 Trade name: ABS-PRO
- **1.2 Use of the product:** 3Dprinter Filament

# 1.3 Supplier:

Ooznest Limited The Yard, Old Crown Lane, Brentwood, Essex, CM14 5TA United Kingdom Phone: 01277 523171 Company Registration No: 09582219

### 2. Hazards identification

# 2.1 Classification of the substance or mixture classification (REGULATION (EC) No 1272/2008)

This product is not classified according to Regulation (EC) 1272/2008 and Directive 67/548/EEC.

# 2.2 Label elements

Not applicable.

# 3. Composition/information on ingredients

# 3.2 Mixtures

None of the substances, named in the Candidate list art. 59 (1,10) of the REACH regulation EC no. 1907/2006 has been used in a concentration > 0,1%.

# 4. First aid measures

# 4.1 Description of first aid measures

General advice:

If you feel unwell, seek medical advice (show the label where possible). Never give anything by mouth to an unconscious person. Take off contaminated clothing and shoes mmediately.

If inhaled:

in case of gases evolving from molten filament, move person into fresh air.

skin contact with molten filament:

rinse well with water. If skin irritation persists, call a physician.

In case of eye contact with molten filament:

If easy to do, remove contact lens, if worn.

In the case of contact with eyes,

rinse immediately with plenty of water and seek medical advice.



According to EU Directive 1907/2006

#### **Product name: ABS-PRO** Date of issue: 31-05-2018

Version: 1.3

If swallowed:

Rinse mouth with water. Induce vomiting immediately and call a physician. If a person vomits when lying on his back, place him in the recovery position.

# **4.2 Most important symptoms and effects, both acute and delayed** no data available

**4.3** Indication of any immediate medical attention and special treatment needed no data available

5. Fire fighting measures

### 5.1 Extinguishing media

Suitable extinguishing media: Water spray, Dry chemical agents, Carbon dioxide (CO2).Foam Unsuitable extinguishing media : Do not use a solid water stream as it may scatter and spread fire.

# 5.2 Special hazards arising from the substance or mixture

In case of fire may be liberated: carbon monoxide and carbon dioxide (CO2).

### 5.3 Advice for fire fighters

Fire fighting measures

Wear a self-contained breathing apparatus and chemical protective clothing. Unusual Fire Hazards:

Standard procedure for chemical fires. Use extinguishing measures that are appropriate to local circumstances and the surrounding environment. In the event of fire and/or explosion do not breathe fumes.

#### 6. Accidental release measures

**6.1 Personal precautions, protective equipment and emergency procedures** Avoid breathing gases from molten filament. Ensure adequate ventilation, especially in confined areas.

#### 6.2 Environmental precautions

Do not allow to enter public sewers and watercourses.

**6.3** Methods and materials for containment and cleaning up Use mechanical handling equipment. Keep in suitable, closed containers for disposal. Clean contaminated surface thoroughly.

# 7. Handling and storage

#### 7.1 Handling

Avoid contact with molten material. Use general dilution ventilation and/or local exhaust ventilation to control airborne exposures

#### Prevention of Fire and Explosion:

Not available

7.2 Conditions for safe storage, including any incompatibilities Keep container closed.

Safa	- Atv Data Shoot		
	ety Data Sheet rding to EU Directive 1907/2006		
	duct name: ABS-PRO		
Date o	of issue: 31-05-2018	accurace in order to evold eintering	Version: 1.3
	Protect from direct sunlight and all heat Store container in a well dry/cool place.	sources in order to avoid sintering.	
	Keep away from waterways and sewers		
	Keep away from any source of ignition.		
Other	precautions:		
	Avoid contamination of foods.		
	Avoid inhalation of dust during the proce	essing of the resin	
8. Ex	posure controls/personal protection		
	· · · · ·		
8.1	Control parameters Dnel: Dnel/Dmel- values are r	act available	
	PNEC: PNEC- values are not a		
3.2	Exposure controls		
-			
-			
_	Engineering measures Provide adequate ventilation while printi	ing.	
	Engineering measures Provide adequate ventilation while printi	ing.	
	Engineering measures	ing.	
9. Ph	Engineering measures Provide adequate ventilation while printi hysical and chemical properties Information on basic physical and ch	emical properties	
9. Ph	Engineering measures Provide adequate ventilation while printi <b>aysical and chemical properties</b> Information on basic physical and che Appearance	emical properties Solid Filament	
9. Ph	Engineering measures Provide adequate ventilation while printi sysical and chemical properties Information on basic physical and che Appearance Odour	emical properties Solid Filament Neutral	
9. Ph	Engineering measures Provide adequate ventilation while printi sysical and chemical properties Information on basic physical and che Appearance Odour Colour	e <b>mical properties</b> Solid Filament Neutral depending on product grade	
9. Ph	Engineering measures Provide adequate ventilation while printi sysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold	emical properties Solid Filament Neutral depending on product grade No information available	
9. Ph	Engineering measures Provide adequate ventilation while printi sysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH	emical properties Solid Filament Neutral depending on product grade No information available Not applicable	
9. Ph	Engineering measures Provide adequate ventilation while printi pysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ -	
9. Ph	Engineering measures Provide adequate ventilation while printi sysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH	emical properties Solid Filament Neutral depending on product grade No information available Not applicable	
9. Ph	Engineering measures Provide adequate ventilation while printi <b>hysical and chemical properties</b> <b>Information on basic physical and ch</b> Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable	
9. Ph	Engineering measures Provide adequate ventilation while printi sysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas)	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable Not applicable No information available	
9. Ph	Engineering measures Provide adequate ventilation while printi sysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available	
9. Ph	Engineering measures Provide adequate ventilation while printi pysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or explosive limits	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available LEL: No data available	
9. Ph	Engineering measures Provide adequate ventilation while printi pysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or explosive limits Vapour pressure	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available LEL: No data available Not applicable	
9. Ph	Engineering measures Provide adequate ventilation while printi pysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or explosive limits Vapour pressure Vapour density	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available LEL: No data available Not applicable Not applicable Not applicable	
9. Ph	Engineering measures Provide adequate ventilation while printi pysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or explosive limits Vapour pressure Vapour density Relative density	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available LEL: No data available Not applicable Not applicable Not applicable Not applicable Not applicable Not measured	
9. Ph	Engineering measures Provide adequate ventilation while printi psical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or explosive limits Vapour pressure Vapour density Relative density Solubility(ies)	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available LEL: No data available LEL: No data available Not applicable Not applicable Not applicable Not measured Not measured	
9. Ph	Engineering measures Provide adequate ventilation while printi Pysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or explosive limits Vapour pressure Vapour density Relative density Solubility(ies) Partition coefficient (n-octanol/water)	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available LEL: No data available LEL: No data available Not applicable Not applicable Not measured Not measured Not available	
9. Ph	Engineering measures Provide adequate ventilation while printi <b>hysical and chemical properties</b> <b>Information on basic physical and che</b> Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or explosive limits Vapour pressure Vapour density Relative density Solubility(ies) Partition coefficient (n-octanol/water) Auto-ignition temperature	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available LEL: No data available LEL: No data available Not applicable Not applicable Not applicable Not measured Not measured	
9. Ph	Engineering measures Provide adequate ventilation while printi Pysical and chemical properties Information on basic physical and che Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or explosive limits Vapour pressure Vapour density Relative density Solubility(ies) Partition coefficient (n-octanol/water)	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available LEL: No data available LEL: No data available Not applicable Not applicable Not measured Not measured Not measured Not available not self-igniting	
	Engineering measures Provide adequate ventilation while printi <b>hysical and chemical properties</b> <b>Information on basic physical and che</b> Appearance Odour Colour Odour threshold pH Melting/freezing point Initial boiling point and boiling range Flash point Evaporation rate Flammability (solid, gas) Upper/lower flammability or explosive limits Vapour pressure Vapour density Relative density Solubility(ies) Partition coefficient (n-octanol/water) Auto-ignition temperature Decomposition temperature	emical properties Solid Filament Neutral depending on product grade No information available Not applicable 140~170°C/ - Not applicable No information available Not applicable No information available UEL: No data available LEL: No data available LEL: No data available Not applicable Not applicable Not measured Not measured Not measured Not available not self-igniting >280 °C	

**10.1 Reactivity:** The product is stable and non-reactive under normal conditions of use, storage and transport.

booznest
----------

According to EU Directive 1907/2006

### Product name: ABS-PRO

Date of issue: 31-05-2018

Version: 1.3

#### **10.2** Chemical stability: Stable under recommended storage conditions.

### **10.3** Possibility of hazardous reactions:

No decomposition or hazardous reactions if stored and applied as directed.

### 10.4 Conditions to avoid:

Avoid elevated temperatures for prolonged periods of time.

#### **10.5** Incompatible materials: Materials to avoid: Strong oxidizing materials.

#### **10.6 Hazardous decomposition products** Build-up of dangerous/toxic fumes possible in cases of fire/high temperature.

11. Toxicological information

# 11.1 Information on toxicological effects

Acute toxicity: Skin corrosion/irritation: Serious eye damage/eye irritation: Respiratory or skin sensitization: Reproductive toxicity: Carcinogenicity: Not known. Not irritating. No data available. No sensitization. Negative. No data available.

# 12. Ecological information

- **12.1 Toxicity** No data available.
- 12.2. Persistence and degradability
  - Difficult to degrade.
- 12.3 Bioaccumulative potential No data available.
  12.4 Mobility in soil
- No data available
- **12.5 Results of PBT and vPvB assessment** No data available.
- **12.6 Other adverse effects** No data available.

# 13. Disposal considerations

# 13.1 Waste treatment methods

Advice on disposal and packaging: Disposal in accordance with local and national regulations.

# 14. Transport information



According to EU Directive 1907/2006

**Product name: ABS-PRO** Date of issue: 31-05-2018

Version: 1.3

14.1	UN number
	Not regulated as a hazardous material.
14.2	UN proper shipping name
	Not applicable
14.3	Transport hazard class(es)
	Not applicable
14.4	Packing Group
	Not applicable
14.5	Environmental hazards
	No additional data is available

- 14.6 Special precautions for user No data available
- 14.7. Transport in bulk according to Annex II of MARPOL73/78 and the IBC Code Not evaluated

15. Regulatory information

# 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

EU regulation (EC) 1907/2006 (Reach) ANNEX XVII (restrictions) Not applicable.

# 15.2 Chemical Safety Assessment

Chemical safety assessments for substances in this mixture were not carried out

# 16. Other information

Information is referenced from other manufacturers.

For abbreviations and acronyms, see: ECHA Guidance on information requirements and chemical safety assessment, chapter R.20 (Table of terms and abbreviations).

This safety data sheet complies with the requirements of Regulation (EC) No. 1907/2006 and Regulation (EC) No. 2015/830. Label element according to Regulation (EC) No 1272/2008.

The information provided in this Safety Data Sheet is correct to the best of our knowledge, information and belief at the date of its publication. The information given is designed only as a guidance for safe handling, use, processing, storage, transportation, disposal and release and is not to be considered a warranty or quality specification. The information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process, unless specified in the text.